## XINXIANG KOLANKY



The leader of oilfield drilling and cementing chemicals

# **Cement Spacer KOL SP CEM**

#### **PROPERTY**

KOL SP CEM is a dusting agent that made of some high active surface active agents, suspending agent weighting agent thinner and the others addition agents.

#### **BASIC DATA**

Appearance	Fineness	Temperature Renge
Free flow powder or granule	≤10.0	25~150°C (BHCT)
	(0.425mm sieve residue), %	

### **TECHNICAL DATA**

Items	Specification	Cement slurry formulations
Moisture content, %	≤10.0	G cement, W/C: 0.44 Water quality: tap water. Sample dosage: 5% SP (BWOC)
Initial consistency, Bc	≤30	
Thickening time,	>60	
min/80°C.46.5Mpa.45min	≥00	
Density difference, g/cm3	≤0.05	
Compression strength,	>7	
Mpa/80°C. normal pressure.24h	≥7	

#### **FEATURE**

It can be formulated in a different proportion of release agent on request,  $1.0 \sim 1.9 \, \text{g} \, / \, \text{cm}3$ 

It's non-toxic, odorless, non-corrosive.

It is formulated isolation solution can effectively replace, washing mud, cement slurry and mud to prevent cross-contamination.

Formulated spacer fluid and the cement slurry has good compatibility, can effectively dilute slurry and improve performance.

### **PACKAGE & STORAGE**

Sacked with three packages, 25kg/sack.

Be kept away from moisture and possible damage of the packages in transportation .St orage life is two years.

Tel: 86-373-5270048 Email:info@oilfield-chem.com Web: www.oilfield-chem.com