

# Moderate Temperature Cement Retarder

# **KOL RTD-ML CEM (Liquid)**

## **PROPERTY**

KOL RTD-ML CEM is consists of compounds such as glucose acid salt and hydroxy carboxylic acid. It can absorb on the surfaces of cement hydrate to inhibit contact with water and on the surfaces of crystal nucleus to prevent their increase. So it can retard hydrating of cement slurry.

#### **BASIC DATA**

Appearance	Specific gravity	Dosage	Operation temperature
Colorless clear liquid	1.08g/cm <sup>3</sup>	0.06%~1.0% (BWOC) Increase the dosage with the temperature rise appropriately	75℃~100℃ (BHCT)

## **TECHNICAL DATA**

Itoms	Specification	Cement slurry
Items		formulations
Initial consistency, Bc/80°C,46.5MPa.45min	≤30	G cement, W/C 0.44,
Adjustable thickeningtime	adjustable	Water quality:distilled
Free fluid, %	≤1.4	water
Compression strength,Mpa,/102°C,21Mpa,24h	≥14	

## **FEATURE**

It's non-poisonous, without odor or corrosively.

Reduce consistency of cement slurry and improve the rheology.

It can prolong the slurry thickening time effectively.

It 's generally used in oil wells between the temperature ranges.

It's sensitive, should be measured accurately when using.

# PACKAGE & STORAGE

Be stored in 25Kg/barrel.

Be kept away from damage and leakage in store and transportation. Stored in cool and dry situation.